

Foamaster[®] WO 2390

(old: Dehydran[®] P 3290)



general	antifoam/defoamer for styrene-butadiene latex
chemical nature	silicone free formulation based on white oil, alkyl polyalcoxyesters and ethers

Properties

physical form	hazy amber liquid								
shelf life	When stored under the usual appropriate storage conditions, the product can be stored for 1 year.								
typical properties (no supply specification)	<table><tr><td>density at 20 °C (68 °F)</td><td>~ 0.93 g/cm³</td></tr><tr><td>Brookfield viscosity at 23 °C (73 °F)</td><td>~ 900 mPa.s</td></tr><tr><td>dilution appearance (10%, 30 mn)</td><td>~ 5%</td></tr><tr><td>odor</td><td>a little intrinsic odor</td></tr></table>	density at 20 °C (68 °F)	~ 0.93 g/cm ³	Brookfield viscosity at 23 °C (73 °F)	~ 900 mPa.s	dilution appearance (10%, 30 mn)	~ 5%	odor	a little intrinsic odor
density at 20 °C (68 °F)	~ 0.93 g/cm ³								
Brookfield viscosity at 23 °C (73 °F)	~ 900 mPa.s								
dilution appearance (10%, 30 mn)	~ 5%								
odor	a little intrinsic odor								

Application

Foamaster[®] WO 2390 is a defoamer for styrene-butadiene polymerization, specifically during monomer “stripping”. Foamaster[®] WO 2390 is silicone-free and does not have adverse secondary effects during latex application.

recommended concentrations	The dosage is generally 0.01 – 0.20% on latex. When used as a defoamer for monomer “stripping”, we recommend to prepare an aqueous dilution (2 – 10% in water).
-----------------------------------	---

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of the BASF Group, unless otherwise noted

BASF SE
Formulation Additives
67056 Ludwigshafen, Germany
www.dispersions-pigments.basf.com
formulation-additives-asia@basf.com
formulation-additives-europe@basf.com
formulation-additives-nafta@basf.com
formulation-additives-south-america@basf.com