

FoamStar® SI 2216

(old: Dehydran® 1650)



general defoamer for aqueous systems; especially suitable for solvent-free and binder-free pigment pastes, industrial wood coatings and pigmented UV-curable coats

chemical nature organically modified polysiloxanes

Properties

physical form clear colorless to slightly turbid liquid

shelf life When stored under the usual appropriate storage conditions, the product can be stored for 2 years.

**typical properties
(no supply specification)**

density at 20 °C (68 °F)	~ 0.94 g/cm ³
flash point	> 100 °C (212 °F)
solubility	emulsifiable

Application

FoamStar® SI 2216 exhibits excellent defoaming properties in aqueous paint systems without impairing gloss development. It produces superior results in solvent-free and binder-free pigment pastes containing a high proportion of dispersing agent, as well as in clear and pigmented industrial and UV-curable coating formulations. FoamStar® SI 2216 gives excellent rapid foam-knockdown performance coupled with long-term stability.

recommended concentrations In pigmented systems, FoamStar® SI 2216 should be added to the mill-base in order to ensure thorough mixing. Even in clear coat formulations, good mixing is necessary to achieve the desired effect. Typical dosage levels depend on the coating system used, but usually are 0.05 – 1.50% calculated on total formulation.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of the BASF Group, unless otherwise noted

BASF SE
Formulation Additives
67056 Ludwigshafen, Germany
www.dispersions-pigments.basf.com
formulation-additives-asia@basf.com
formulation-additives-europe@basf.com
formulation-additives-nafta@basf.com
formulation-additives-south-america@basf.com