#### **Technical Information**

# Efka® FL 3600

(old : Efka® 3600 N)



general slip and leveling agent

Efka® FL 3600 reduces the surface tension of organic coating systems. This and good compatibility make it a very effective anti-cratering and

flow control agent.

**chemical nature** polymeric fluorocarbon compound

## **Properties**

physical form slightly yellowish liquid

**shelf life**The product should be stored in a cool dry place. When kept in its

original unopened containers, it will keep up to 4 years.

typical properties active ingredients 100%

(no supply specification) solvent methoxypropyl acetate

density at 20 °C (68 °F) ~ 1.075 g/cm<sup>3</sup>

color  $\leq 4$ 

### **Application**

Efka® FL 3600 is especially suitable for

- · baking enamels based on alkyd, acrylic or polyester resins
- polyurethane coatings
- two-pack epoxy coatings
- air-drying alkyd systems

## recommended concentrations

0.1-1.0% on total formulation

Efka® FL 3600 should be added at the end of the batch preparation.

#### Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

#### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

 $^{\circledR}$  = registered trademark,  $^{\intercal M}$  = trademark of the BASF Group, unless otherwise noted

BASF SE
Formulation Additives
67056 Ludwigshafen, Germany
www.dispersions-pigments.basf.com
formulation-additives-asia@basf.com
formulation-additives-europe@basf.com
formulation-additives-nafta@basf.com
formulation-additives-south-america@basf.com